



# LATAPOXY® 310 Rapid Stone Adhesive

DS-679.3-0314

**Globally Proven  
Construction Solutions**



## 1. PRODUCT NAME

LATAPOXY® 310 Rapid Stone Adhesive

## 2. MANUFACTURER

LATICRETE International, Inc.  
1 LATICRETE Park North  
Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 235  
Toll Free: 1.800.243.4788, ext. 235  
Fax: +1.203.393.1684  
Internet: [www.laticrete.com](http://www.laticrete.com)

## 3. PRODUCT DESCRIPTION

LATAPOXY 310 Rapid Stone Adhesive is a fast setting two component, high strength epoxy adhesive, which is formulated for the spot bonding of tile and stone installations on vertical surfaces. LATAPOXY 310 Rapid Stone Adhesive maintains its non-sag consistency at high temperatures up to 95°F (35°C).

### Uses

- Spot bonding marble, granite, adhered masonry veneer and large format ceramic tile on walls and overheads, interior or exterior applications.
- Ideal for fireplace surrounds, elevators and stair risers.
- Adhesive for bedding and fastening marble, granite and other stone slabs on walls and wainscoting.
- Adhesive for fabricating granite, marble and other stone.
- Approved by TCNA for Interior applications method W215 and W260

### Advantages

- Fast Permanent Bond—5–8 minutes.

- Easy to Use—1:1 mixing ratio by volume.
- Non-Staining—ideal for white and light colored—marbles, other stones and tiles.
- Withstands shock and vibration.
- Durable Permanent Bond—will not deteriorate over time.
- Safe—no solvents.
- Non-Sag—when applied up to 1" (25 mm) thick.
- Approved by the following building code bodies for exterior installations: ICC and IBC.

### Acceptable Substrates

Please consult LATICRETE Technical Services at 1.800.243.4788, ext. 230 for specific installation details.

### Interior Substrates

- Concrete
- Concrete masonry units (CMU)
- Brick/masonry
- Exterior glue plywood
- Cement backer board\*
- Steel\*\*

\* Consult cement backer board manufacturer for specific installation recommendations.

\*\*Steel surface must be cleaned to remove oil, dust oxidation and other bond inhibiting materials.

### Exterior Substrates

Please consult LATICRETE Technical Services at 1.800.243.4788, ext. 235 for approval prior to use for all exterior applications. There is a maximum height restriction of 30 ft (9.1 m). For exterior installations outside of North America, contact the LATICRETE International Department at 1.800.243.4788, ext. 242.

- Concrete
  - Must be minimum 6" (150 mm) thick reinforced
  - Must be minimum 3500 psi (24 MPa)
  - Must be minimum 28 days old prior to installation
- CMU
  - Double wythe walls only

### Packaging

- Mini Unit—2 gal (8 l) kit containing the following:
  - 8 mini jars of Part A, 0.13 gal (0.5 l)
  - 8 mini jars of Part B, 0.13 gal (0.5 l)
- Full Unit—2.6 gal (10 l) kit containing the following:
  - 1.3 gal (5 l) Part A pail
  - 1.3 gal (5 l) Part B pail
- Commercial Unit—2.6 gal (10 l) each Part A and Part B pails
- Cartridge Packs—2.3 gal (9 l) containing the following:
  - 15 cartridge packs of Part A and Part B
  - For use in LATAPOXY 310 Cordless Mixer

### Cartridge Pack Coverage

One carton (15 cartridges) will yield approximately 150 ft<sup>2</sup> (14 m<sup>2</sup>) with 1/4" (6 mm) thick dabs, or 300 ft<sup>2</sup> (27 m<sup>2</sup>) with 1/8" (3 mm) thick dabs when covering 10% of the veneer surface.

### Coverage

The coverage for LATAPOXY® 310 Rapid Stone Adhesive will vary depending upon the amount of product required to plumb the wall. The chart below is based on 10% coverage of the area of each tile or stone piece:

| Average Inches Out of Plumb | LATAPOXY® 310 Thickness | Approx. Coverage/ 10 Liter Unit                 |
|-----------------------------|-------------------------|---|
| Plumb Wall                  | 1/8" Thick (3 mm)       | 300–325 ft <sup>2</sup> (27–30 m <sup>2</sup> ) |
| 1/4" (6 mm)                 | 1/4" Thick (6 mm)       | 150–170 ft <sup>2</sup> (14–16 m <sup>2</sup> ) |
| 1/2" (12 mm)                | 1/2" Thick (12 mm)      | 75–80 ft <sup>2</sup> (7–7.5 m <sup>2</sup> )   |

### Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years if stored at >32°F (0°C) to <110°F (43°C).

### Limitations

- Surface temperature for application: 50°F (10°C)–95°F (35°C).
- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Sandstone, slate and fissile stones are not recommended veneers and should not be used with LATAPOXY 310 Rapid Stone Adhesive. These stones and other porous stones may delaminate or break apart due to the nature of their porous and layered composition.
- Note:** Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or, L/480 for thin bed stone installations or L/600 for exterior veneers where L=span length (except where local building codes specify more stringent deflection requirements)
- DO NOT bond to particle board, luan, fire-retardant plywood, marine grade plywood, Masonite®, any chemically treated plywood or hardwood surfaces.

### Cautions

Consult MSDS for more safety information.

- Keep out of reach of children.
- LATAPOXY 310 Rapid Stone Adhesive has a slight, non-hazardous odor.
- During cold weather, protect finished work from traffic until fully cured.
- LATAPOXY 310 Rapid Stone Adhesive Part A is corrosive to eyes and skin before curing. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Consult local building code for requirements.

## 4. TECHNICAL DATA

### Physical Properties

| Test                                     | Test Method                    | Results                          | Specification        |
|--|--------------------------------|----------------------------------|----------------------|
| 14 day Marble to Concrete Shear Strength | ANSI A118.3 5.5 <sup>^</sup>   | >950 psi (6.5 MPa) <sup>^^</sup> | N/A                  |
| Compressive Strength                     | ANSI A118.3 5.6                | 8900–9400 psi (61.4–64.8 MPa)    | >3500 psi (24.1 MPa) |
| Tensile Strength                         | ANSI A118.3 5.7                | 1300–2000 psi (9–13.7 MPa)       | >1000 psi (6.9 MPa)  |
| Thermal Shock                            | ANSI A118.3 5.8 <sup>^^^</sup> | 1100–1600 psi (7.6–11 MPa)       | >500 psi (3.45 MPa)  |

Data From TCA-179-01

<sup>^</sup> modified

<sup>^^</sup> tile failure

<sup>^^^</sup> modified to use porcelain tile

| Test  | Test Method       | ISO 13007-1 R2 Specification   | Results                      |
|---|-------------------|--|------------------------------|
| 7 day cure shear adhesive strength                              | ISO 13007-2 4.3.4 | 2 MPa (290 psi)  | 18 – 33 MPa (2610–4785 psi)  |
| 7 day cure 21 day water immersion shear adhesive strength       | ISO 13007-2 4.3.5 | 2 MPa (290 psi)  | 14–34 MPa (2030–4930 psi)    |
| 7 day cure 4 100°C boiling water cycles shear adhesive strength | ISO 13007-2 4.3.8 | 2 MPa (290 psi)  | 22–36 MPa (3190–5220 psi)    |
| Open time after 20 minutes                                      | ISO 13007-2 4.1   | 0.5 MPa (73 psi)   | 2.8–3.8 MPa (406–551 psi)    |
| Slip  | ISO 13007-2 4.2   | Less than or equal to 0.5 mm (0.02 in)                               | 0.1–0.3 mm (0.0039–0.012 in) |
| Transverse deformation  | ISO 13007-2 4.5   | Greater than or equal to 2.5 mm (0.1 in) and less than 5 mm (0.2 in) | 3.2–3.6 mm (0.13–0.14 in.)   |

## 5. INSTALLATION

### Preparation

Before using, store resins at room temperature >70°F (>21°C) for 24 hours to ensure ease of mixing. All surfaces must be sound, clean, free of oil, waxes, frost, curing agents, form release agents or other bond inhibiting contaminants. All substrates must be clean and dry when applying LATAPOXY 310 Rapid Stone Adhesive. Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification AN-3.8 "Requirements for Expansion Joints" or TCA Detail EJ171—Current Year "Expansion Joints". **DO NOT** cover expansion joints with mortar. Finished veneers equipped with any type of resin, mesh, epoxy or fiberglass backing must be ground in those areas to receive LATAPOXY 310 Rapid Stone Adhesive.

Clean and grind back of stone in areas to receive the LATAPOXY 310 Rapid Stone Adhesive spots using a mechanical wheel grinder with a diamond wheel/blade. Remove dust with a stiff brush and wipe entire surface. Using a damp sponge (not wet), wipe the tile or stone to remove any particles or remaining dust to ensure a clean

direct bond and that all ground material is removed. Wipe dry with a clean cloth, then apply LATAPOXY® 310 Rapid Stone Adhesive.

### Recommended Guidelines for Spot Bonding Stone:

(Please consult your Local Code for actual code compliance)

1. Stone or Interior Tile Applications
  - Thickness – units shall not exceed 2" (50mm).
  - Facial Dimensions – maximum of 720 in2 (0.46m2) and no greater than 36" (915mm) along any edge or dimension.
  - Module Weight – 15 lb/ft2 (73 kg/m2) unless otherwise approved by project engineer.
2. Porcelain Tile (exterior)
  - Thickness – units shall not exceed 5/8" (16mm).
  - Facial Dimensions – maximum of 432 in2 (0.28m2) and no greater than 24" (610mm) along any edge or dimension.
  - Module Weight – 9 lb/ft2 (44.2 kg/m2) unless otherwise approved by project engineer.

*Note: Always check with the tile or stone manufacturer to make sure the tile or stone is suitable for wall installations.*

### Mixing

Combine equal volumes of LATAPOXY 310 Rapid Stone Adhesive Part A and Part B (1:1 mix ratio by volume). Mix until uniform in color; no swirls. Mix only as much as can be used in 3–5 minutes. Small quantities can be mixed with a putty knife or margin trowel. Cartridge packs are designed for use only with the LATAPOXY 310 Cordless Mixer and must be at least 65°F (18°C) for proper mixing and dispensing.

### Application

Apply dabs evenly distributed on back of the stone or tile; 5 dabs minimum, 1 in each corner and 1 in center. Cover at least 10% of the area of each piece. Finished dab thickness must be a minimum of 1/8" (3 mm) and a maximum of 1" (25 mm).

Approximate dab diameter required to achieve 10% coverage with 5 dabs:

| Tile Size                   | Dab Diameter |
|-----------------------------|--------------|
| 12" x 12" (300 mm x 300 mm) | 2" (50 mm)   |
| 24" x 24" (600 mm x 600 mm) | 4" (100 mm)  |
| 36" x 36" (900 mm x 900 mm) | 6" (150 mm)  |

After installation of LATAPOXY 310 Rapid Stone Adhesive onto the back of the veneer, install onto substrate and adjust for plumb and level.

### Joint Treatment

**Exterior applications**—Use LATASIL™ to treat all joints for all exterior applications. Refer to DS 6200.1 for further instructions.

**Interior applications**—The following LATICRETE® products may be used for joint treatment on interior applications:

- SPECTRALOCK® PRO Premium Grout  
United States Invention Patent No.: 6881768 (and other Patents)
- SPECTRALOCK PRO Premium Grout
- PERMACOLOR® Grout
- 1500 Sanded Grout or 1600 Unsanded Grout mixed with 1776 Grout Enhancer
- LATASIL

Test area to ensure proper filling as narrow veneers and wider gaps behind the veneer may not allow for joint filling with an epoxy or cement grout.

*Note: Control, expansion or other movement of joints must be treated with a flexible sealant.*

## 6. AVAILABILITY AND COST

### Availability

LATICRETE and LATAPOXY materials are available worldwide.

### For Distributor Information, call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line Distributor information, visit LATICRETE at [www.laticrete.com](http://www.laticrete.com).

### Cost

Contact a LATICRETE Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM

DS 230.13: LATICRETE Product Warranty (United States and Canada)

A component of:

DS 025.0APD: LATICRETE 25 Year Tile & Stone System Warranty (United States and Canada)

DS 025.0SPD: LATICRETE 25 Year System Warranty –MVIS (United States and Canada)

## 8. MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline (hours 8:00 AM to 5:30 PM EST):

Toll Free: 1.800.243.4788, ext. 235

Telephone: +1.203.393.0010, ext. 235

Fax: +1.203.393.1948

### Technical and Safety Literature

To acquire technical and safety literature, please visit our website at [www.laticrete.com](http://www.laticrete.com).

## 10. FILING SYSTEM

Additional product information is available on our website at [www.laticrete.com](http://www.laticrete.com). The following is a list of related documents:

- DS 230.13: LATICRETE® Product Warranty (United States and Canada)
- DS 025.0APD: LATICRETE 25 Year Tile & Stone System Warranty (United States and Canada)
- DS 025.0SPD: LATICRETE 25 Year System Warranty –MVIS (United States and Canada)
- DS 256.0: 1500 Sanded Grout
- DS 258.0: 1600 Unsanded Grout
- DS 685.0: SPECTRALOCK® PRO Grout  
United States Invention Patent No.: 6881768 (and other Patents)
- DS 679.0: LATAPOXY® 310 Stone Adhesive
- DS 6200.1: LATASIL™
- DS 265.0: 1776 Grout Enhancer
- DS 250.0: PERMACOLOR® Grout
- DS 681.0: SPECTRALOCK PRO Premium Grout
- DS 683.0: Cordless Mixer

---

LATICRETE International, Inc.  
One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • [www.laticrete.com](http://www.laticrete.com)

©2014 LATICRETE International, Inc.  
All trademarks shown are the intellectual properties of their respective owners.