

# DUPONT™ STONETECH® PROFESSIONAL BULLETPROOF® SEALER

## TECHNICAL DATA SHEET



### PRODUCT BENEFITS

- Maximum protection against most stains
- Best suited for porous stones
- Preserves natural look
- Interior and exterior use
- Water-based formula

### RECOMMENDED SURFACES

Natural stone such as honed or textured marble, granite, limestone, travertine, sandstone, saltillo and bluestone.

### AVAILABLE SIZES

Pint, Quart, Gallon, 5 Gallon\*

### COVERAGE

Up to 900 sq ft per gallon for a single coat application.

### EXPECTED WEAR

Up to 5 years on interior surfaces and up to 3 years on exterior surfaces.

### TECHNICAL INFORMATION

Form:	Liquid
Specific Gravity:	1.013
HMIS Rating:	2,0,0
Flash Point:	NA
Freeze Point:	32 °F (0 °C)
pH:	8-9

### VOC CONTENT

<400 g/L (excluding water) for EPA purposes.

<120 g/L (including water) for U.S. state purposes (Low Solids Coating).

\*Size not available for sale in all areas

### DIRECTIONS

Read entire label before using. Use only as directed. Always test in a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Allow new grout installations to cure for a minimum of 72 hours prior to application. Make sure surface is clean and free of waxes and coatings. Sealer may be applied to damp surfaces one hour after standing water has been removed. Surface temperature should be between 50 °F and 80 °F (10 °C and 26.7 °C). Ensure that the area is well-ventilated during application and until the surface is dry. Keep children and pets out of the area until treated surface is dry.

1. Ensure cap is closed and sealed, and shake well before use.
2. Mask off surfaces not intended to be treated.
3. Liberally apply an even coat using a paint pad, roller, brush or low-pressure sprayer.
4. Allow sealer to penetrate the surface for 10–15 minutes. During this time, keep the surface wet with sealer, adding more sealer as needed. **DO NOT ALLOW SEALER TO COMPLETELY DRY ON THE SURFACE.**
5. A second coat may be needed for porous, absorbent surfaces. If a second coat is required, it should be applied 30–40 minutes after the initial application as directed in steps 3–4.
6. Following the final application, thoroughly wipe dry the entire surface with clean absorbent towels.
7. Should a sealer residue appear, rewet the impacted section of the surface with sealer. Agitate the surface with a white nylon scrubbing pad to loosen residue and wipe dry with a clean, absorbent towel.
8. A full cure is achieved in 24–72 hours. Use of the treated surface may resume in 6–8 hours. If use of the surface must resume sooner, cover the treated surface with red rosin paper to protect it until full cure has been achieved.
9. Clean tools used during application with water.

### STORAGE AND HANDLING INSTRUCTIONS

Avoid prolonged exposure to vapors. Use in a well-ventilated area. Do not ingest. Avoid contact with eyes and skin. **KEEP OUT OF THE REACH OF CHILDREN.** Do not freeze or store above 100 °F/38 °C. Do not mix with other chemicals. Do not release to natural waterways.

### EMERGENCY/FIRST AID PROCEDURES

**Ingestion:** Do not induce vomiting. Call poison control center. Call a physician.

The DuPont™ StoneTech® Professional product line complies with all federal, state and local VOC regulatory requirements.

PROTECT

CLEAN

TRANSFORM

DuPont™ StoneTech® Professional  
2520 Barrington Court  
Hayward, CA 94545

Technical Support: 888-786-6343

Customer Service: 877-786-6383

[www.stonetechpro.com](http://www.stonetechpro.com)



The miracles of science™

*The information is furnished free of charge and based on information that DuPont believes to be generally reliable and accurate. Individual facts and circumstances may differ. It is intended for your use at your own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.*

*Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, StoneTech®, and BulletProof® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.*

K-20502-2 (03/14)